

Cement Mill Test Report



Mountain Cement Company
 5 Sand Creek Rd
 Laramie, WY 82070
 (307) 745-4879
 www.mountaincement.com



Cement Classification: ASTM C150 Type I/II, AASHTO M85 Type I/II
 Manufacture Period: September 2022

C150 Chemical Requirements – Table 1

Item	Spec Limit	Result
Al ₂ O ₃	6.0 Max	4.0
Fe ₂ O ₃	6.0 Max	3.1
MgO	6.0 Max	0.9
SO ₃	3.0 ^A	3.1
L.O.I.	3.5 Max	1.7
Insoluble Res	1.5 Max	0.9

C150 Physical Requirements – Table 3

Item	Spec	Limit	Result	
Blaine Specific Surface, m ² /kg	C204	260 Min	404	
Air Content of Mortar, Vol %	C185	12 Max	6.8	
Vicat Initial Time of Set, min	C191	45 Min	98	
Vicat Final Time of Set, min	C191	375 Max	197	
Compressive Strength, psi:	C109			
		3 Days	1740 Min	3920
		7 Days	2760 Min	4690

Compound Composition

Item	Spec Limit	Result
C ₃ A, %	8 Max	5
Equivalent Alkalies, %	N/A	0.69
Inorg Proc Addt's, %	5.0 Max	0
CaCO ₃ in Limestone, %	70 Min	88.8
Limestone Additions	5.0 Max	2.0
C1038 Expansion, %	0.020% Max ^B	0.010 ^C

Additional Data

Limestone	Amount (%)	Base Cement Phase Comp	Result
	2.0	C ₃ S (%)	63
	12.5	C ₂ S (%)	14
	2.9	C ₃ A (%)	6
	1.8	C ₄ AF (%)	10
	49.7	CaO (%)	
	5.0	SO ₃ (%)	

ASTM C150 Optional Requirements – Table 4

Item	Spec Limit	Result
C452 Sulfate Resistance, 14 Days, % expansion	0.040 max	0.022 ^C

^A N/A - In compliance with Footnote D, Table 1, ASTM C150 and AASHTO M85.

^B Required only if percent SO₃ exceeds the limit in Table 1

^C Test result for this production period not available. Most recent test result provided.

This cement has been sampled and tested in accordance with ASTM standard methods and procedures. Cement chemical analysis are reported as oxides, in accordance with ASTM Test Method C114. This cement is manufactured at our Laramie, Wyoming facility. All test results are certified to comply with the type and specification designated. We are not responsible for improper use or workmanship.

Bob Kersey, Quality Control Manager

